


GUY WIRE ROPE

HOT DIP GALVANIZED STRAND

SPECIFICATION: ASTM A 475



NOMINAL DIAMETER	CONSTRUCTION	NOMINAL DIAMETER OF WIRES	APPROX WEIGHT	MIN BREAKING STRENGTH	WEIGHT OF ZINC COATING (GRADE A)	STOCK NUMBER
				SEWENSMARTIN		
INCH		INCH	LEBSFT	LEBS	OZ/SQFT	
3/16"	1X7	0.062	0.073	1,900	0.50	H02
1/4"	1X7	0.080	0.121	3,150	0.60	J02
5/16"	1X7	0.109	0.205	5,350	0.80	K02
3/8"	1X7	0.120	0.273	6,950	0.80	L02
7/16"	1X7	0.145	0.399	9,350	0.90	M02
1/2"	1X7	0.165	0.516	12,100	0.90	N02
1/2"	1X19	0.100	0.504	12,100	0.70	N12



Wire rope products will break if abused, misused, or Overused. Regular inspection and maintenance are necessary. Consult industry recommendations and applicable codes before using.

